

App. No. 10/065,738
Amendment dated May 26, 2004
Reply to Office action of December 29, 2003

Amendments to the Claims:

This listing of claims will replace the prior version of the claims in the present application.

Listing of Claims:

Claim 1 (canceled)

Claim 2 (canceled)

Claim 3 (currently amended): The A Faraday rotator set forth in claim 1, wherein said having wavelength selectivity, for selectively rotating only the polarization plane of incident light of given wavelengths, the Faraday rotator comprising:

a magneto-optical section is constituted from a gadolinium iron garnet thin films in between which at least one dielectric layer is interlaminated to create at least two magneto-optical parts for rotating the polarization plane of incident light of at least two wavelengths traveling in the direction in which the magnetic field of said magneto-optical section is oriented; and

dielectric multi-layer films in which a low refractive-index layer and a high refractive-index layer are laminated in alternation, disposed on each side of said magneto-optical section in an arrangement together with said magneto-optical section predetermined to create a resonant structure for localizing within said magneto-optical section incident light of at least two wavelengths.

Claim 4 (currently amended): The Faraday rotator set forth in claim [[1]] 3, wherein said dielectric multi-layer film is composed by laminating in alternation an oxide of silicon as a low refractive-index layer, and an oxide of titanium as a high refractive index layer.

App. No. 10/065,738
Amendment dated May 26, 2004
Reply to Office action of December 29, 2003

Claim 5 (currently amended): The Faraday rotator set forth in claim [[1]] 3, wherein said magneto-optical section and said dielectric multi-layer films are formed integrally by a vapor-phase process.

Claim 6 (canceled)

Claim 7 (canceled)

Claim 8 (currently amended): ~~The An optical isolator set forth in claim 6, wherein~~ said having wavelength selectivity, for selectively blocking only return beams from incident light of given wavelengths, the optical isolator comprising:

a magneto-optical section is constituted from a gadolinium iron garnet thin films in between which at least one dielectric layer is interlaminated to create at least two magneto-optical parts for rotating the polarization plane of incident light of at least two wavelengths traveling in the direction in which the magnetic field of said magneto-optical section is oriented;

a magnetic part for applying a magnetic field to said magneto-optical section;
dielectric multi-layer films in which a low refractive-index layer and a high refractive-index layer are laminated in alternation, disposed on each side of said magneto-optical section in an arrangement together with said magneto-optical section predetermined to create a resonant structure for localizing within said magneto-optical section incident light of at least two wavelengths

a polarizer for extracting polarized components from incident beams; and
an analyzer utilized in combination with said polarizer.

Claim 9 (canceled)

App. No. 10/065,738

Amendment dated May 26, 2004

Reply to Office action of December 29, 2003

Claim 10 (currently amended): The optical isolator set forth in claim [[6]] 8, wherein said dielectric multi-layer films are composed by laminating in alternation an oxide of silicon as a low refractive-index layer, and an oxide of titanium as a high refractive index layer.

Claim 11 (currently amended): The optical isolator set forth in claim [[6]] 8, wherein said polarizer and said analyzer are lent a structure having distributed refractive indices, by irradiating with either a particle beam or an energy beam a diamond-like carbon thin film along a bias with respect to the film's thickness direction.

Claim 12 (original): The optical isolator set forth in claim 11, wherein said particle beam is an ion beam, an electron beam, a proton beam, α -rays, or a neutron beam; and said energy beam is light rays, X-rays or γ -rays.

Claim 13 (currently amended): The optical isolator set forth in claim [[6]] 8, wherein said magneto-optical section, said magnetic part, said dielectric multi-layer films, said polarizer, and said analyzer are formed integrally by a vapor-phase process.

Claim 14 (original): A polarizer lent a characteristic structure having distributed refractive indices, by irradiating with either a particle beam or an energy beam a diamond-like carbon thin film along a bias with respect to the film's thickness direction.

Claim 15 (original): The polarizer set forth in claim 14, wherein said particle beam is an ion beam, an electron beam, a proton beam, α -rays, or a neutron beam; and said energy beam is light rays, X-rays or γ -rays.

Claim 16 (currently amended): An amorphous diamond-like carbon thin film incorporating hydrogen, characterized in being transparent in the light region, and in having

App. No. 10/065,738
Amendment dated May 26, 2004
Reply to Office action of December 29, 2003

an extinction coefficient that is 3×10^{-4} or less at optical-communications wavelengths of from 1200 nm to 1700 nm.

Claim 17 (currently amended): An optics component, characterized by utilizing the amorphous diamond-like carbon thin film set forth in claim 16.

Claim 18 (original): The optical isolator set forth in claim 11, wherein said diamond-like carbon thin film is transparent in the light region, and has an extinction coefficient that is 3×10^{-4} or less at optical-communications wavelengths of from 1200 nm to 1700 nm.

Claim 19 (original): The optical isolator set forth in claim 12, wherein said diamond-like carbon thin film is transparent in the light region, and has an extinction coefficient that is 3×10^{-4} or less at optical-communications wavelengths of from 1200 nm to 1700 nm.

Claim 20 (original): The polarizer set forth in claim 14, wherein said diamond-like carbon thin film is transparent in the light region, and has an extinction coefficient that is 3×10^{-4} or less at optical-communications wavelengths of from 1200 nm to 1700 nm.

Claim 21 (original): The polarizer set forth in claim 15, wherein said diamond-like carbon thin film is transparent in the light region, and has an extinction coefficient that is 3×10^{-4} or less at optical-communications wavelengths of from 1200 nm to 1700 nm.